



CORPORATE PURCHASING SPECIFICATION

AA 220 06

Rev.No. 03

PAGE 1 of 5

RESIN IMPREGNATED DENSIFIED LAMINATED WOOD TYPE VI

1. GENERAL :

This specification governs the quality requirements of a Resin Impregnated wood based laminate, consisting of layers of 1 mm thick wood veneers impregnated under vacuum and/or pressure with synthetic resin and further bonded and densified under heat and pressure. The synthetic resins is usually phenol/cresol formaldehyde type. It has good mechanical and electrical properties with resistance to corrosion and termite attack.

The grain and fibre disposition of the constituent veneers shall be more or less equal in each axis, at right angle to each other, so as to have compressive strength in direction of its thickness and rigidity. The material in insulating oil has temperature index of at least 105.

2. APPLICATION :

Used as guide block clamps, stator winding support rings, nuts etc. for Generators, Transformer & Switch gear.

3. COMPLIANCE WITH NATIONAL STANDARDS :

The material shall comply, in general, with the requirements of the following National Standards and also meet the requirements of this specification.
IS:3513 (Part I)- 1989 : Specification for Resin Treated Compressed Wood Laminates (Comregs)- For electrical Purposes

4. DIMENSIONS AND TOLERANCES :

Shall be as stated on the order/drawing.

5. FINISH :

The machined edges of boards and the surface of components shall be finished with a high viscosity varnish conforming to IS:10026, Pt-3, - Sec.1 and the surface shall be free from checks, splits, blisters, discoloration, gaps, open joints etc.

COPYRIGHT AND CONFIDENTIAL
The information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED.
It must not be used directly or indirectly in any way detrimental to the interest of the company.

Revisions: Ref: Clt 29445 of MOM of MRC(E)			Approved: INTERPLANT MATERIAL RATIONALISATION COMMITTEE - MRC (E)		
Rev.No. 03	Amd.No.	Reaffirmed	Prepared BHOPAL	Issued CORP. R&D	Dt. of 1st Issue Feb 80
Dt. 1-1-98	Dt.	Year:			

**6. TEST SAMPLE:**

The test sample shall be supplied in finished shape and size in accordance with IS: 3513 and shall be prepared from the same batch. Wherever possible the sample shall be cut from components.

7. PROPERTIES:

Unless otherwise specified, testing shall be done in accordance with the relevant methods of IS: 3513.

7.1 PHYSICAL:**7.1.1 Density:**

1.25 g/cm³, min.

7.1.2 Moisture Content and Volatile Matter:

4%, max.

7.1.3 Water Absorption:

2%, max.

Finished test specimens of size 40 x 40 x 12 mm prepared from the same batch, shall be submerged in water at 27 ± 2°C for 24 hours.

7.2 Mechanical:**7.2.1 Tensile Strength (AA 085 17 01):**

90 N/mm², min.

7.2.2 Cross Breaking Strength:

95 N/mm², min.

7.2.3 Comprehensive Strength:

Perpendicular to laminate : 185 N/mm² min.
Parallel to Laminate : 120 N/mm² min.

The test shall be carried out on 20 x 20mm x thickness of board. However, thickness above 20 mm shall be machined down to 20 mm keeping one side intact.

7.3 Electrical:**7.3.1 Electric Strength (1 minute-Proof) in oil at 90 ± 2°C:**



CORPORATE PURCHASING SPECIFICATION

AA 220 06

Rev.No. 03

PAGE 3 of 5

Flatwise : 4 kV/mm for 6 mm thick specimen

Edgewise : 25 kV for 25 mm wide specimen.

8. EFFECT OF OIL ON WOOD (TYPE TEST) :

8.1 Sludge and Oil Acidity (Appendix -1):

8.1.1 Increase in Acidity : 0.1 mg KOH/g, max.

8.1.2 Increase in Sludge Content : 0.05%, max.

9. TEST CERTIFICATES :

Unless otherwise stated, three copies of test certificates shall be sent along with each consignment.

In addition, the supplier shall ensure to send one copy of test certificates along with the despatch documents to facilitate quick clearance of the material.

The test certificates shall bear the following information:

AA 22006 : Resin Impregnated Densified Laminated
(Rev.No.3) Wood type VI, Revision 01.

BHEL Order No.

Manufacturer's/Suppliers Name

Batch/Lot No.

Trade mark, if any

Quantity supplied

Test results for clauses 4,7 and 8.

10. PACKING AND MARKING :

The components/boards shall be suitably packed to prevent damage during transit. Each package shall bear the following information :

AA 22006 : Resin Impregnated Densified Laminated
Wood Type VI.

BHEL Order No.

BHEL Drawing No/Type No.

Manufacturer's Name & Grade.

Thickness, Width & Length.

No. of components/boards

Net weight & Gross weight.

11. REFERRED STANDARDS(Latest Publications Including Amendments):

1. IS: 3513

2. IS: 100 26, Pt-3

3. AA 085 17 01



Appendix -I

Sludge and Oil Acidity:

1. Conditioning: Condition the test piece for 168 hours in controlled atmosphere of $65 \pm 5\%$ RH and $27 \pm 2^\circ$ C.
2. Test Specimen: Cut the specimen to dimension of 75mm x 12.5mm x Thickness.

NOTE: Thickness above 9 mm shall be machined to 9 mm. Both the surfaces shall be machined evenly to achieve thickness of 9mm.

3. Procedure: Into a 150 mm x 25 mm test tube weigh 25 g of transformer oil. Transformer oil complying with the requirements of IS 335 is suitable. Prepare the test specimen, weigh it to the nearest 0.01 g and introduce it into the oil. Lightly plug the mouth of the tube with cotton wool and place it in a constant temperature bath maintained at $100 \pm 0.5^\circ$ C for 164±1 hour.

Place a similar quantity of the same oil in a second tube and maintain this under the same conditions as a 'blank' sample.

At the end of the specified heating period, remove the tubes from the bath and allow them to cool to room temperature. If it can be seen that delamination has occurred, the specimen has failed. If there is no visible delamination, determine the sludge content of the oil in which the pressboard has been immersed as follows.

Pour the oil into a 600 ml beaker and wash the test tube and pressboard sample with n-heptane until oil-free, adding the washings to the oil in the beaker. Make the contents of the beaker upto approximately 300 ml with n-heptane. Cover the beaker with a watch glass and allow to stand in the dark for 24 hrs. at room temperature.

Filter the solution through a tared, dried, sintered glass filter, of no. 4 filter transferring all the sediment to the filter with the aid of n-heptane from a wash-bottle. Dry the filter at $105 \pm 2^\circ$ C to constant mass. Express the amount of sediment as a percentage of the original sample mass.

Make the filtrate up to 500 ml in a measuring cylinder with n-heptane. Make the 'blank' sample up to 500 ml in a second cylinder. Determine the acid values of the heptane solutions as follows.



CORPORATE PURCHASING SPECIFICATION

AA 220 06

Rev.No. 03

PAGE 5 of 5

Place 60 ml toluene and 40 ml industrial methylated spirits (66 overproof) in a 600 ml conical flask. Add 2 ml to 3 ml Alkali blue 6B indicator solution (2% by mass in industrial methylated spirits and one drop of 0.1N hydrochloric acid). Neutralize this mixture, with 0.1N alcoholic potassium hydroxide (KOH), to give a red colour which persists for 15 s. Add 100 ml of the above filtrate to the neutralized solvents and titrate to the same end point with the 0.1N alcoholic KOH. Repeat the titration on 100 ml of the 'blank' solution.

Results: Calculate the increase in the acid value of the oil per gram of pressboard in mg KOH//g from the expression:

$$\text{increase in acid value} = \frac{(t_2 - t_1) \times 5.61 \times 5}{W}$$

Where

t_1 is the number of millilitres of 0.1N KOH required to neutralize 100 ml n-heptane in blank solution;

t_2 is the number of millilitres of 0.1N KOH required to neutralize 100 ml of filtrate; and

W is the sample mass of laminated pressboard (grams).

Report the acid value of the 'blank' oil together with the increase in acid value due to the sample as calculated from the above equation. Report also the percentage sludge produced by the sample.