



TME/2011

PRODUCT STANDARD

TME DIVISION, BHOPAL

TM 14553

Rev. No. 00

PAGE 01 OF 02

PRODUCT STANDARD FOR NON ASBESTOS, MOISTURE RESISTANT, SLATE FILLED, SOLVENTLESS PUTTY

1. Scope:

This specification describes about a non-asbestos, moisture resistant slate filled solvent less putty made of two part material (One part : powder and one part: Resin) mixed in given proportion and used in filling voids and spaces in traction motor armatures and field coils.

2. Mixing guidelines:

The two parts (One part: powder and one part: Resin) to be mixed at the time of application in a ratio as recommended by supplier and converted to a tough infusible solid by heat.

3. Properties of resin:

Property	Unit	Specified value	Test method
Type of resin	-	Solvent less resin	-
Colour	-	Clear liquid (preferably)	-
Viscosity	CPS	300-400	Brook field apparatus
Storage life below 20°C	Months	6 months (minimum)	-
Gel time at 100°C with 1% catalyst	Minutes	15-30	-
Density at 25°C		1.19±0.01	
Flash point	°C	Above 200	

4. Curing Cycle for putty:

8 Hrs when cured at 90°C/6 Hrs when cured at 125°C/4 Hrs when cured at 150°C or any other curing cycle as recommended by supplier

5. Properties of cured putty:

Property	Unit	Specified value	Test method
Physical state at room temperature	-	Solid	-
BDV of 3mm thick specimen at room temperature	KV/mm	10 (minimum)	JIS-K-6911 CL5.8 & IS2504/BS2782
Insulation Resistance	Ω CM	1.9 x 10 ¹³ at room temperature (minimum)	IS11755
		1.8 x 10 ¹³ at 125 °C (minimum)	
Dissipation factor, 500V	-	0.012 at room temperature	JIS-K-6911
		0.02 at 125 °C	
Dielectric Constant	-	4.3	JIS-K-6911 CL5.14.1
Class of Insulation		Class H (minimum)	IEC-216-1 to 5
Pot life at room temperature	hrs	72 (minimum)	-

Rev. No. 00

Distribution

Prepared

Checked

Approved

Date: 29.10.2014

TME - 2 TNX - 1
TXM - 1 TAM - 1
QMX - 1 TSD - 1

(Shishu Pal)

(V.Rawtiya)

(S.P.Singh)

COPYRIGHT AND CONFIDENTIAL
The information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED
It must not be used directly or indirectly in any way detrimental to the interest of the company

6



TME/2011

PRODUCT STANDARD
TME DIVISION, BHOPAL

TM 14553

Rev. No. 00

PAGE 02 OF 02

COPYRIGHT AND CONFIDENTIAL
The information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED
It must not be used directly or indirectly in any way detrimental to the interest of the company

6. Test Certificate:

Supplier to submit 2 copies of test certificate for resin and cured putty with each consignment.

Test certificate shall bear following information:

**TM14553: NON ASBESTOS, MOISTURE RESISTANT, SLATE FILLED,
SOLVENTLESS PUTTY**

BHEL PO NO:

Batch No. /Lot No:

Test values obtained w.r.t. specification:

7. Packing & Marking:

Each package shall be marked with following information:

**TM14553: NON ASBESTOS, MOISTURE RESISTANT, SLATE FILLED,
SOLVENTLESS PUTTY**

BHEL PO NO:

Batch No. /Lot No:

Month and year of manufacturing: