

1. NAME OF COMPONENT –**SUPPORTING BOARD**
2. DRAWING NO. -5056167
3. MATERIAL –**PHEN LAM PAPER BASE SHT.**

TENSILE STRENGTH: For sheets above 1.5mm and above: 70 N/mm², min.

4. SIZE – 12 X 30 X 430 LG.
5. WEIGHT –0.214 Kg

SPECIAL TREATMENT -When a specimen is immersed in hot oil at 110 degree C for 24 hours, it shall not show any sign of splitting, blistering, disintegration or appreciable warping

When a test piece of 100 x 100mm of ordered thickness is kept at 125 degree C for 24 hours And then cooled, it shall not show any sign of crumbling, cracking or blistering.

FIG.

